



SAB LABS
ISO/IEC 17025 Accredited Services Provider
Worldwide Accepted Testing Report

TEST REPORT
00541-26

REPORT ISSUE DATE
08-Jul-2026

Overall Rating: See the Results

Reporting and Client Provided Information

Client Name	Brookfield Industries
Address	Next to Awan Hospital Pasrur Road, Sialkot, Pakistan
Contact Number	Mr. Ahsan Raza
Email	-
Sample Receiving Date	01-Jul-2026
Reporting Date	08-Jul-2026
Sample Description	Working and Welding Gloves
End Use	-
Fiber Content	Cow Split leather, Cowhide Leather, Goat Leather
Style/Item	SL11119, SL11120, SL11104, SL11117
Weight	-
Buyer Name	-
Color Name	Red, Blue, Black, Yellow
Quality	-
Size	-
Lot#	-

Signed for and on behalf of
SAB LABS

Manager Lab





SAB LABS

ISO/IEC 17025 Accredited Services Provider
Worldwide Accepted Testing Report

TEST REPORT
00541-26

REPORT ISSUE DATE
08-Jul-2026

Summary of Test Report

Test Name	Test Results
EN 388	S

P: Pass

F: Fail

S: See the Results



SAB LABS

ISO/IEC 17025 Accredited Services Provider
Worldwide Accepted Testing Report

TEST REPORT
00541-26

REPORT ISSUE DATE
08-Jul-2026

Leather Garden Gloves (Art # SL 11117)

1-Protective Gloves Against Mechanical

EN 388:2016+A1:2018

Clause	Test Parameters	Results				Performance Level
6.1	Abrasion Resistance (Cycles)	Trail 1	Trail 2	Trail 3	Trail 4	3
		2000	2280	2187	2167	
6.2	Blade Cut Resistance (Index)	Index 1		Index 2		1
		1.76		1.88		
		1.45		2.09		
		2.10	Mean 1.94	1.94	Mean 2.02	
		1.98		2.22		
		2.45		1.98		
6.4	Tear Strength Resistance (N)	Trail 1 Direction 1	Trail 2 Direction 2	Trail 2 Direction 1	Trail 2 Direction 2	2
		45.4	43.59	42.34	42.56	
6.5	Puncture Resistance(N)	Trail 1		Trail 2		1
		50.99		52.66		

Leather Tactical Gloves (Art # SL 11104)

2-Protective Gloves Against Mechanical

EN 388:2016+A1:2018

Clause	Test Parameters	Results				Performance Level
6.1	Abrasion Resistance (Cycles)	Trail 1	Trail 2	Trail 3	Trail 4	3
		5000	5500	4500	5200	
6.2	Blade Cut Resistance (Index)	Index 1		Index 2		3
		5.98		4.88		
		5.45		5.09		
		5.10	Mean 5.24	4.94	Mean 5.08	
		4.98		5.22		
		4.75		5.28		
6.4	Tear Strength Resistance (N)	Trail 1 Direction 1	Trail 2 Direction 2	Trail 2 Direction 1	Trail 2 Direction 2	3
		70.6	61.43	71.02	59.88	
6.5	Puncture Resistance(N)	Trail 1		Trail 2		2
		78.45		79.12		

MEB Street, Plot no.1-D-2, ST/9, Sector 16-B, North Karachi Industrial Area, Karachi Pakistan
SAB LABS 179/A Block F-2 Pak Arab Housing Society Ferozpur Road Lahore
(Tel:021-36912530) e-mail ihsan.raza@sablabs.net web: www.sablabs.net



SAB LABS

ISO/IEC 17025 Accredited Services Provider
Worldwide Accepted Testing Report

TEST REPORT
00541-26

REPORT ISSUE DATE
08-Jul-2026

Leather Welding Gloves (Art # SL 11119, 11120)

2-Protective Gloves Against Mechanical

EN 388:2016+A1:2018

Clause	Test Parameters	Results				Performance Level
6.1	Abrasion Resistance (Cycles)	Trail 1	Trail 2	Trail 3	Trail 4	4
		8000	8100	8200	8000	
6.2	Blade Cut Resistance (Index)	Index 1		Index 2		3
		6.28		5.98		
		5.99		6.39		
		5.76	Mean 6.00	5.94	Mean 6.07	
		6.22		6.19		
		5.78		5.88		
6.4	Tear Strength Resistance (N)	Trail 1 Direction 1	Trail 2 Direction 2	Trail 2 Direction 1	Trail 2 Direction 2	4
		118.0	76.23	116.43	75.88	
6.5	Puncture Resistance(N)	Trail 1	Trail 2			4
		156.89	161.34			

Notes: Uncertainty of Measurement

Clause 6.1 Abrasion Resistance	N/A
Clause 6.2 Coup Cut, Blade Cut Resistance	N/A
Clause 6.4 Tear Resistance	±1%
Clause 6.5 Puncture Resistance	±1%

The estimated uncertainty of measurement for the test results is based on a standard uncertainty multiplied by a Coverage factor k=2, which provides for a confidence level of approximately 95%.

Test Item	Performance Level					
	0	1	2	3	4	5
Abrasion Resistance (EN 388) Number of cycles (minimum)	<100	100	500	2000	8000	---
Blade Cut Resistance (EN 388) Index (I) (minimum)	<1.2	1.2	2.5	5.0	10.0	20.0
Tear Resistance (EN 388) Force (N) (minimum)	<10	10	25	50	75	---
Puncture Resistance Force (N)	<20	20	60	100	150	---



SAB LABS

**ISO/IEC 17025 Accredited Services Provider
Worldwide Accepted Testing Report**

**TEST REPORT
00541-26**

**REPORT ISSUE DATE
08-Jul-2026**

Sample Pictures



Sampling was not performed by SAB Laboratory does not accept the responsibility that the sample (s) supplied is / are truly representative sample(s) of any batch or stock or the entire production. This report shall not be reproduced wholly or in parts, without the written approval of the laboratory. This test report solely based on the particular sample(s) supplied by the party / client, however, after completion of the report, the samples will be preserved for three months. Non-accredited Scope of testing is also included.

END OF THE TEST REPORT

**MEB Street, Plot no.1-D-2, ST/9, Sector 16-B, North Karachi Industrial Area, Karachi Pakistan
SAB LABS 179/A Block F-2 Pak Arab Housing Society Ferozpur Road Lahore
(Tel:021-36912530) e-mail ihsan.raza@sablabs.net web:www.sablabs.net**